

| | | |
|---|---|----------------------|
| Composition Composición | 80% SDA - 20% Polyester AT 80% SDA - 20% Poliester AT | Uses Usos |
| Width Ancho | 20 mm | |
| Weight Peso | 16 g/m ² | |
| Thickness Grosor | 1'5 mm | |
| Finish Acabado | Water repellent. Anti-stain treatment Hidrófugo con tratamiento anti-manchas | Qualities Cualidades |
| Colour fastness to light Solidez a la luz | 7/8 UNE EN ISO 105-B02:2014 | |
| Colour fastness to artificial weathering Solidez del color a la intemperie artificial | 4/5 UNE EN ISO 105-B04:1998 | |
| Colour fastness to rubbing Solidez de las tinturas al frote | 4-5/5 UNE EN ISO 105-X12:2016 | |
| Colour fastness to chlorinated water Solidez de las tinturas al agua clorada | 5/5 UNE EN ISO 105-E03:2010 | |
| Ultraviolet protection factor UPF Factor de protección ultravioleta UPF | 50+ AZ/NZS 4399/1996 | |
| Spray test | 5/5 UNE EN ISO 24920 | |
| Water column mm Columna de agua mm | 100 UNE EN ISO 20811 | |
| Breaking Streght Resistencia a la rotura | 5500 N UNE EN ISO 13934-1:2013 | |
| Resistance to pilling Resistencia al pilling | 4/5 UNE EN ISO 12945-2:2001 | |
| Abrasion resistance (Martindale) Resistencia a la abrasión (Martindale) | 20000 UNE EN ISO 12497-2:2016 | |
| Cleaning instructions Manutención | | |
| | | |
| | | |
| | | |
| | | |
| | | |
| | | |

Sensitive values of tolerance +/- 5% Valores susceptibles de tolerancia de +/- 5%



The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations. La garantía Agora cubre un anormal deterioro del tejido debido a la pérdida de color o resistencia siempre que existan unas condiciones de exposición normales, incluyendo el sol, moho, putrefacción y químicos de la atmósfera en general, siempre y cuando el tejido haya sido instalado, utilizado y mantenido correctamente. La garantía no cubre los trabajos de instalación del distribuidor. La garantía tampoco cubre, en cualquier caso, el deterioro debido al uso abusivo, quemaduras accidentales, negligencia o perforación.